

FRANZ MIEDERHOFF OHG Röhre 50 D-59846 Sundern

23.04.2010

Plastigum 50.5002.00

Application: special adhesive for artificial (PVC) leather and soft PVC. For manufacturing folding roofs for sport cars. For glueing and concealing in the foil sector. Can also be used as a two component adhesive together with H 15 hardener.

Basic raw materials: polyurethane elastomer, synthetic resins, solvent

Colours: colourless, transparent

Consistency: brush able

Density (20° C): approx. 0,85 g/ cm³

Solid contents: approx. 19%

Flash point: below +21° C, easily inflammable, keep away from open flames and sparks

Storage: at 15° -25° C in unopened original packs for 1 year

Frost resistance: adhesive will freeze, can be used again after adjustment to room temperature and thawing

Resistant to: water, softeners, diluted acids and alkaline solutions

Heat resistance: will stand temperatures of approx. +70°C , with the addition of 10% H 15 hardener up to +100°C

Cleaning agent: VD 1 thinner

Drying time: can be handled immediately after glueing. Maximum adhesion is reached after 48 hours

ADR: transport according to the rules of limited quantities. Products packed in compound packing are not dangerously classified.

This product information sheet can only give general advice and cannot result in liability on our part.

FRANZ MIEDERHOFF OHG
Franz Miederhoff
Metall- u. Kunststoffwarenfabrik
59833 Sundern - Postfach 1352
59846 Sundern Röhre 50

Franz Miederhoff oHG Sitz Sundern Amtsgericht-Registergericht Arnsberg HRA 1410

Volksbank Sauerland eG
Dresdner Bank, Sundern
Postbank, Dortmund

Nr. 219206900 (BLZ 46660022)
Nr. 796249600 (BLZ 44080050)
Nr. 31393468 (BLZ 44010046)

IBAN: DE17 4666 0022 0219 2069 00 Swift-BIC: GENODEM1NEH
IBAN: DE44 4408 0050 0796 2496 00 Swift-BIC: DRES DE FF 467
IBAN: DE85 4401 0046 0031 3934 68 Swift-BIC: PBNKDEFF

www.miederhoff.de
contact@miederhoff.de