



## STRATIFICATION KIT

**Contains: 250 g of polyester resin, 5 g of hardener, 1 band of taffeta 1.10 ML x 9 cm**  
**Ideal for small repairs on polyester (boats, windsurfers ...)**

---

### PHYSICAL CHARACTERISTICS

Color: ..... Grey green  
Thickness: ..... About 1.15 g/ml  
Preparation time: ..... 4.7 minutes

---

### PREPARATION OF THE SURFACE

The surface must be clean, dry and dust free. Free oil and grease, sand well before treatment.

---

### PREPARATION OF THE PAINT

Mixing ratio: Resin 98 % + Hardener 2 %  
Do not put more than 3 % hardener and less than 1.5 %

---

### APPLICATION

Mix the resin with hardener. Apply evenly over the surface to be treated. Spread the band taffeta. Apply by pressing with a brush for example. Then, apply a new layer of resin. After about 20 minutes, we can apply the putty polyester normally.

---

### CHARACTERISTICS FOR USE

Do not use at temperatures below 5°C. The ideal temperature of treatment is between 15 and 20°C.

---

### PACKING AND STORAGE

Packaging: ..... 250g  
9 months in unopened.  
Recommended storage temperature 5 – 35°C. Protect against freezing.

---

### PRECAUTIONS FOR USE

Use protective gloves, masks and clothes.  
Work in a ventilated area; an accumulation of solvents can catch fire if exposed to a naked flame or a spark.

---

### HEALTH AND SAFETY

See data sheet

---

*This information corresponds to the actual state of our knowledge and has the sole object of informing you about our products and possible applications. It is objectively given but does not imply any guarantee by us.  
Our company may modify all these details at any time*